

DT17A Double-Sided Nickel/Copper Fabric Tape

NI/CU DOUBLE-SIDED CONDUCTIVE FABRIC TAPE

Laird Technologies' DT17A double-sided conductive fabric tape is constructed of nickel/copper metallized fabric with conductive pressure sensitive adhesives (PSA) on both sides. This reliable tape provides XYZ-axis electrical conductivity, EMI shielding performance, a well-balanced design in adhesion, flame retardant, and thermal conductivity.

DT17A is RoHS compliant and halogen free. It's good for EMI/RFI shielding to electronic devices.

FEATURES <a>RoHs

- RoHS compliant
- Halogen-free per IEC-61249-2-21 standard
- Shielding effectiveness of >70 dB across a wide spectrum of frequencies

MARKETS

- Cabinet applications
- LCD and Plasma TV

- Laptop computers

Medical equipment

- Servers
- Printers

COMPOSITION OF PRODUCT

Die Cut







USA: +1.866.928.8181 Europe: +49.0.8031.2460.0 Asia: +86.755.2714.1166



DT17A Double-Sided Nickel/Copper Fabric Tape

ltem	Unit	Value	Test Method
Thickness	mm	0.17 ± 0.02	-
Peel Adhesion	Kgf / 25 mm	>1.4	PSTC 101*
Shear Adhesion			
at R.T.	Hrs	>168	PSTC 107#
at 80°C	Hrs	>5	PSTC 107#
Tensile Strength	Kgf / 25 mm	>15	
Operation Temperature	°C	0-80	-
Flammability	-	Pass	UL510-FR method [^]
Z-axial Resistance	Ω	<0.08	-
Thermal Resistance at 50°C/10 psi	°C-in²/W	0.9 typical	ASTM D5470
Far-field Shielding ⁺			IEEE-299 (modified)
30 MHz to 300 MHz	dB	76	
300 MHz to 3 GHz	dB	89	
3 GHz to 18 GHz	dB	87	
Package Dimensions (Max. Width: 1000 mm)	М	W: Dimension by Customer Spec L: Standard Length of 20 M	
Shelf Life (Under 23°C/65% R.H.)		One Year	

*:Test Method C, dwell time 30 min. #:Contact area 25 mm by 25 mm ^:Internal Test +: Typical Value

APPLICATION TECHNIQUES

- 1. Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure develops better adhesive contact & thus improves bond strength.
- 2. To obtain optimum adhesion, the bonding surfaces must be clean, dry and well unified. A typical surface cleaning solvent is isopropyl alcohol. Use proper safety precautions for handling solvents.
- 3. Ideal tape application temperature range is 21°C to 38°C. Initial tape application to surfaces at temperatures below 10°C is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

EMI-DS-FOF-DT17A 0414

Any information furnished by Laird Technologies, Inc. and its agents is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird Technologies materials rests with the end user. Laird Technologies materials or products for any specific or general uses. Laird Technologies materials or products for any specific or general uses. Laird Technologies Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2013 Laird Technologies, Inc. and Itaird Technologies. Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2013 Laird Technologies, Inc. All Rights Reserved. Laird Laird Technologies, Inc. and Flaird Technologies, Inc. and Technologies, Inc. and Flaird Technologies, and the marks or registered trade marks or Laird Technologies, Inc. and Flaird Technologies, Inc. and Flaird